



Customer: THE GARDEN FURNITURE CENTRE LTD **Test Report No:** 176236

Test Results

***Solar UV Protective Properties for Textile Material (EN 13758-1:2001+A1:2006)**

Test conditions

- 1 Air temperature: 21±1°C
- 2 Relative humidity: 65±2% R.H.
- 3 Orientation of test specimen: Specimens were clamped on sample holder. Fabric face side is facing the incident UV light.
- 4 Test conducted in wavelength range 290-400 nm
- 5 Instrument: UV-VIS Spectrophotometer
- 6 No. of Scans: 8

Test sample: Sample AR - As Received

Test results:

Number of specimens:	1	2	3	4	5	6	7	8	Mean
Mean UVA transmission (%):	0.23	0.21	0.29	0.29	0.27	0.30	0.21	0.32	0.27
Mean UVB transmission (%):	0.05	0.05	0.09	0.08	0.08	0.11	0.05	0.10	0.08
Mean UPF:	1555	1700	873	940	1024	745	1605	778	1152
Std. Deviation:									398.66
Std. Error:									332.64
Sample UPF:									>50

Comment: Sample complies with the UPF 40+ requirement

Remarks :

1. According to EN 13758-2:2003+A1:2006, in order to fulfill the requirement, below criteria should be met:
The clothing assembly shall have the lowest UPF value larger than 40 and average UV-A transmission smaller than 5%. Clothing assembly meet design requirement.
2. The results given apply only to the colour and weight of fabric tested. Unless otherwise stated the fabric is tested dry and relaxed.
3. This UPF Rating is for the fabric and does not address the amount of protection which is afforded by the design of the article. The manipulations involved in garment manufacture such as stretching and sewing may lower the UPF of the material.
4. The protection offered by this fabric may be lessened :
 - (i) At points where the fabric is in close contact with the skin such as across the shoulders
 - (ii) If the fabric is stretched
 - (iii) If the fabric is wet; and
 - (iv) With time due to effects of normal wear.
5. For headwear: The item does not provide protection against reflected or scattered solar UVR.

Note : Graph is attached

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only